

DuPont™ Delrin®

acetal resin

Delrin® 150 NC010

Delrin® 150 NC010 is a high viscosity acetal homopolymer for extrusion processes. It has excellent thermal stability, low die deposit, and enhanced crystallization for low porosity.

Property	Test Method	Units	Value
Identification			
Resin Identification	ISO 1043		POM
Part Marking Code	ISO 11469		>POM<
Mechanical			
Yield Stress	ISO 527	MPa (kpsi)	72 (10.4)
Yield Strain	ISO 527	%	21
Nominal Strain at Break	ISO 527	%	40
Tensile Modulus	ISO 527	MPa (kpsi)	3100 (450)
Flexural Modulus	ISO 178	MPa (kpsi)	2900 (420)
Notched Charpy Impact Strength	ISO 179/1eA	kJ/m ²	-30°C (-22°F)
			23°C (73°F)
Thermal			
Deflection Temperature 0.45MPa 1.80MPa	ISO 75-1/-2	°C (°F)	166 (331)
			97 (207)
Melting Temperature 10°C/min	ISO 11357-1/-3	°C (°F)	178 (350)

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.

ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.

Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Delrin® are trademarks or registered trademarks of DuPont Company. Copyright© 2006.

061010/061010

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. CAUTION: This product is not permitted to be sold for use in medical applications involving any implantation in the human body or where contact with internal body fluids or tissues will equal or exceed 24 hours. For applications involving contact of less than 24 hours, see "DuPont Medical Caution Statement", H-50102 and contact your DuPont sales representative.

Boedeker Plastics, Inc.
904 West 6th Street
Shiner, Texas 77984
1-800-444-3485
www.boedeker.com

plastics.dupont.com



The miracles of science®

Delrin® 150 NC010

Property	Test Method	Units	Value
Thermal			
CLTE, Parallel	ISO 11359-1/-2	E-4/C (E-4/F)	
-40 - 23°C (-40 - 73°F)			1.0 (0.56)
23 - 55°C (73 - 130°F)			1.1 (0.61)
55 - 100°C (130 - 212°F)			1.4 (0.78)
CLTE, Normal	ISO 11359-1/-2	E-4/C (E-4/F)	
-40 - 23°C (-40 - 73°F)			0.9 (0.5)
23 - 55°C (73 - 130°F)			1.0 (0.56)
55 - 100°C (130 - 212°F)			1.5 (0.83)
Rheological			
Melt Mass-Flow Rate	ISO 1133	g/10 min	
190°C, 2.16kg			2.4
Flammability			
Flammability Classification	IEC 60695-11-10		
1.5mm		HB	
3.0mm		HB	
Flammability Classification	UL94		
1.5mm		HB	
3.0mm		HB	
Temperature Index			
RTI, Electrical	UL 746B	°C	
1.5mm			50
3.0mm			50
RTI, Impact	UL 746B	°C	
1.5mm			50
3.0mm			50
RTI, Strength	UL 746B	°C	
1.5mm			50
3.0mm			85

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.

ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.

Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Delrin® are trademarks or registered trademarks of DuPont Company. Copyright© 2006.

061010/061010

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. CAUTION: This product is not permitted to be sold for use in medical applications involving any implantation in the human body or where contact with internal body fluids or tissues will equal or exceed 24 hours. For applications involving contact of less than 24 hours, see "DuPont Medical Caution Statement", H-50102 and contact your DuPont sales representative.

Boedeker Plastics, Inc.
904 West 6th Street
Shiner, Texas 77984
1-800-444-3485
www.boedeker.com
plastics.dupont.com



Delrin® 150 NC010

Property	Test Method	Units	Value
Other			
Density	ISO 1183	kg/m ³ (g/cm ³)	1420 (1.42)
Water Absorption	ISO 62, Similar to	%	
Immersion 24h			0.39
Molding Shrinkage	ISO 294-4	%	
Normal, 2.0mm			2.0
Parallel, 2.0mm			1.8
Processing - Injection Molding			
Melt Temperature Range		°C (°F)	210-220 (410-430)
Melt Temperature Optimum		°C (°F)	215 (420)
Mold Temperature Range		°C (°F)	80-100 (175-210)
Mold Temperature Optimum		°C (°F)	90 (195)
Hold Pressure Range		MPa (kpsi)	90-110 (13-16)
Processing - Extrusion			
Melt Temperature Range		°C (°F)	195-205 (385-400)
Melt Temperature Optimum		°C (°F)	200 (395)
Processing Moisture Content		%	<0.2
Processing			
Drying Time, Dehumidified Dryer		h	2-4
Drying Temperature		°C (°F)	80 (175)
Processing Moisture Content		%	<0.2

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
 ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.
 Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Delrin® are trademarks or registered trademarks of DuPont Company. Copyright© 2006.

061010/061010

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. CAUTION: This product is not permitted to be sold for use in medical applications involving any implantation in the human body or where contact with internal body fluids or tissues will equal or exceed 24 hours. For applications involving contact of less than 24 hours, see "DuPont Medical Caution Statement", H-50102 and contact your DuPont sales representative.

Boedeker Plastics, Inc.
 904 West 6th Street
 Shiner, Texas 77984
 1-800-444-3485
www.boedeker.com